

# WAKOL MS 245 Montinator

## Technical Information

### Area of application

Single-component elastic mounting adhesive bonding wooden materials, metals, plastics, concrete, stone, decorative tiles, wall cladding, panels and wooden strips. Especially for parquet floorings, baseboards, stair profiles, butt stairs, repair stairs as well as for closing expansion joints.

### Special properties



- solvent-free according to the definition of TRGS 610
- may be coated after hardening
- rapid-hardening
- stable
- reacts with moisture
- simple handling

1) Emission class according to French law

### Technical data

Raw material base:	MS-hybrid-polymer
Cleaning agent:	WAKOL RV 105 Neoprene Dilution before the adhesive dries
Open time:	approx. 5 - 10 minutes
Hardening time:	approx. 24 hours with 2.5 mm.
Temperature stability:	- 40 °C to + 90 °C in hardened state
Method of application:	With suitable cartridge injector.
Storage temperature:	between +5 °C and 25 °C, protect from heat.
Storage time:	12 month at room temperature
Danger classification according to GefStoffV:	see material safety data sheet
GISCODE:	not applicable

### Subfloors

The subfloor as well as the climatic conditions of the room must meet the requirements of DIN 18365. The substrates to be bonded must be free of dust, grease and oil, as well as firm and capable of bearing weight. Sand before-hand as required.

## Usage

Apply WAKOL MS 245 Montinator in bead form on the substrates to be bonded and join within the open time.

## Important

Especially for parquet, skirting boards, stair-profiles, blast-rims, repair-steps as well as for closing connection joints.

WAKOL MS 245 Montinator must not be used below + 5°C and above +40 °C.

Because of the variety of varnish paints and coating materials we advise to pilot tests. Apply the varnish paint within 4 hours to the sealing compound.

We guarantee the uniform high quality of our products. All data is based on tests and many years of practical experience and refers to standardised conditions. The variety of materials used and the different construction site conditions, which lie beyond our control, preclude any claims based on this data. We therefore recommend making sufficient trials. Accompanying flooring manufacturer's instructions and the currently applicable codes must be observed. We gladly provide technical advice.

The product data sheets can be found in their latest version at [www.wakol.com](http://www.wakol.com).

This Technical Information of 22.07.2013 supersedes all previous versions.